

НЕТЕПЛОСТОЙКИЕ СТАЛИ

Доступные формы продукта

 Длинномерные изделия*

 Пластины

*) Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Описание продукта

BÖHLER K455 corresponds approximately to the material 1.2550 (~60WCrV7, ~S1) in terms of the alloy concept. This classic matrix steel is characterized by high toughness, good machinability, and polishability. BÖHLER K455 offers the advantage of simple heat treatment with low hardening temperatures and single tempering. BÖHLER K455 is widely used in the field of punching and cutting tools as well as in the field of embossing tools.

Маршрут плавления

 Airmelted

Свойства

- > Жесткость и пластичность : очень высокий
- > Прочность на сжатие : высокая
- > Размерная стабильность : хорошо

Применение

- > Cold Forming
- > Стандартные детали (пресс-формы, пластины, штифты, штампы)
- > Прессование порошков

Технические данные

Обозначение материала	
~1.2550	SEL
~60WCrV7	EN
~60WCrV8	
~S1	AISI

Химический состав

C	Si	Mn	Cr	V	W
0,63	0,60	0,30	1,10	0,18	2,00

Свойства материала

	Прочность на сжатие	Стабильность размеров при термообработке	Жесткость	Стойкость к абразивному износу
BÖHLER K455	★★★	★	★★★★★	★
BÖHLER K245	★★	★	★★★★★	★
BÖHLER K460	★★★★	★	★★★★	★★
BÖHLER K720	★★	★	★★★★	★

Условие поставки

Annealed

Твердость (HB)	макс. 225
----------------	-----------

Термическая обработка

Annealing

Температура	710 на 750 °C	Slow controlled cooling in furnace at a rate of 50 to 68°F/hr (10 to 20°C/hr) down to approx. 1112°F (600°C), further cooling in air.
-------------	---------------	---


Stress relieving

Температура	650 °C	Slow cooling in furnace. Intended to relieve stresses set up by extensive machining, or in complex shapes. After through heating, hold in neutral atmosphere for 1-2 hours
-------------	--------	--

Hardening and Tempering

Температура	870 на 900 °C	Oil, Holding time after temperature equalization: 15 to 30 minutes. After hardening, tempering to the desired working hardness, see tempering chart.
-------------	---------------	--


Tempering chart



Tempering:

Hardening temperature:
 890°C / 1634°F
 Specimen size: square 20mm


Continuous cooling CCT curves



Austenitising temperature: 880°C / 1616°F
Holding time: 15 minutes


O Vickers hardness
5...35 phase percentages
0.02...14 cooling parameter, i.e. duration of cooling from 800°C to 500°C (1472°F to 932°F) in $s \times 10^{-2}$
10...0.2K/min cooling rate in K/min in the 800°C to 500°C (1472°F to 932°F) range

Quantitative phase diagram




A... Austenite
B... Bainite
K... Carbide
M... Martensite
P... Pearlite
RA... Retained austenite
- - - - Oil cooling
- · - Air cooling
1... Edge or face
2... Core

Isothermal TTT curves




Austenitising temperature: 880°C / 1616°F
Holding time: 15 minutes

Influence of work diameter on core hardness and hardness penetration



Quenched from: 890°C / 1634°F
Agent: Oil

Heat treatment sequence



Физические свойства

Температура (°C)	20
Плотность (kg/dm ³)	8
Теплопроводность (W/(m.K))	25
Удельная теплоемкость (kJ/kg K)	0,46
Удельное электрическое сопротивление (Ohm.mm ² /m)	0,3
Модуль упругости (10 ³ N/mm ²)	210

Тепловое расширение

Температура (°C)	100	200	300	400	500
Тепловое расширение (10^{-6} м/(м.К))	11	12,5	13	13,5	14

Long Products: For additional specifications and technical requirements, please contact our regional voestalpine BÖHLER sales companies.

Sheet & Plates: Product Variant may differ in terms of melting process, technical data, delivery, and surface condition as well as available product dimensions. Please contact voestalpine BÖHLER Bleche GmbH & Co KG.

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.